

Schunk Kohlenstofftechnik GmbH
 Rodheimer Strasse 59
 35452 Heuchelheim, Germany
research.skt@schunk-group.com
www.schunk-group.com

Bulk density	(g/cm ³)	1,40
Porosity	(%)	25
Flexural strength	(MPa)	100
Tensile strength	(MPa)	230
Strain to failure (tension)	(%)	0,5
Strain to failure (flexion)	(%)	0,2
Young's modulus tension	(GPa)	75
flexion		57
Interlaminar shear strength	(MPa)	5
Coefficient of thermal expansion α 1000 °C (1830 °F)	(10 ⁻⁶ /K)	1,0
Specific electrical resistance	($\mu\Omega$ m)	28
Ash	(ppm)	300

eb 06.06

The data shown above are not guaranteed, but typical values based on our experience. It should be understood that a spread of results can occur due to variations in materials and production processes.

Please find the standards for the determination of our material properties at
www.schunk-group.com/skt/dm