



Schunk Kohlenstofftechnik GmbH  
Rodheimer Strasse 59  
35452 Heuchelheim, Germany  
research.skt@schunk-group.com  
www.schunk-group.com

Bulk density	(g/cm <sup>3</sup> )	1.52
Porosity	(%)	22
Flexural strength	(MPa)	25
Compressive strength	(MPa)	50
Hardness Rockwell HR5/40		108
Forming method		isostatic molding

kt 08.08

The data shown above are not guaranteed, but typical values based on our experience. It should be understood that a spread of results can occur due to variations in materials and production processes.

Please find the standards for the determination of our material properties at  
[www.schunk-group.com/skt/dm](http://www.schunk-group.com/skt/dm)